



## ACRY-TECH COATINGS INC.

3601 NE 5<sup>th</sup> Avenue • Ft. Lauderdale, FL 33334

e-mail : sales@acry-tech.com • www.acrytech.com

Design & Manufacture of Architectural & Specialty Coatings

Phone 954-565-6001

Fax: 954-565-2864

TollFree 800-771-6001

# Advantage Elastomeric

**Advantage Elastomeric** provides flexibility, durability & watertight integrity for years of waterproof protection for Tile, Bermuda, Shingle, Poured Concrete, Sloped Gravel Roofs or Flat Roofs (with positive drainage). This product stops leaks thereby eliminating the need for expensive reroofing. The Acry-Tech Elastomeric System has been proven for over 20 years and successfully stood up to Hurricanes Andrew, Floyd and Irene by giving great wind and water resistance to many types of roofing in South Florida and the Bahamas!

**SURFACE PREPARATION:** All surfaces must be free from loose coatings, chalk, biological growth, oil, rust or other contaminants. **New Surfaces:** Fill all cracks and holes with Acry-Tech Filler and then prime all porous surfaces with *Acry-Tech Primer*. **Previously Painted Surfaces:** Pressure clean as above. Repair all holes and cracks with *Acry-Tech Filler*. Prime chalking surfaces with *Acry-Tech Primer*. Apply cement slurry coat if needed as a base coat to fill cracks and gaps between tiles & shingles or over gravel. The slurry will consolidate the surface to provide an even monolithic substrate for elastomeric application. (See instruction packet.)

**APPLICATION:** Apply by airless sprayer, brush or roller and apply generously using overlapping strokes. Do not brush or roll excessively as this induces foam and reduces coating integrity. Textured and porous surfaces will require more coating. A two coat application rate of 100 sf per gallon per coat yields 16 dry mils. A two coat application of 80 square feet per gallon per coat will yield 20 dry mils of waterproof protection. Do not apply this coating to a wet surface, or when rain or evening dew is imminent. Do not apply late in the day or when surface temperature is or will be below 50° F. Wash spills and tools immediately with soapy water.

### TECHNICAL DATA:

Solids By Weight 63%    Solids by Volume 50%    Wt per gallon (#) 11.5    Viscosity 10-15 Kcps

UV Resistance - Excellent    Elongation 700%    Tensile Strength 300psi    Perms (English) 6 (E96-BW)

**HMIS RATINGS:**    **HEALTH 1**    **FLAMMABILITY 0**    **REACTIVITY 0**  
**PERSONAL PROTECTION: HANDLING B**    **APPLICATION G**

**CAUTIONS:** KEEP FROM FREEZING. USE ONLY WITH ADEQUATE VENTILATION. DO NOT TAKE INTERNALLY. CLOSE CONTAINER AFTER EACH USE, KEEP OUT OF THE REACH OF CHILDREN! AVOID EYE CONTACT. WEAR GOGGLES.

**WARRANTY:** No warranty of merchantability or fitness for a particular purpose is given either expressly or implied. ACI will however, replace at its manufacturing facility any of its products which are determined by ACI to have a manufacturing defect.